

TECHNICAL DATA SHEET

Product: 8801

Colour: White

Structure: Keyback

Composition: 80% Fibre/20% Binder

Fibre Composition: 75% Viscose/25% Polyester

PRODUCT SPECIFICATIONS

Test	Orientation	Units	Targets	Range	Methods
Weight			GSM	45	TM 1150
Dry Tensile Strength	MD		N/12plies	450	TM 1005
Dry Tensile Strength	CD		N/12plies	65	TM 1009
Wet Tensile Strength	CD		N/12plies	40	TM 1010
Thickness			mm/4plies	1.3	TM 1031
Sink Time			s	< 2	TM 1015
Absorption capacity			%	900	TM 1016
OV.01 17/Dec/2025					

Plant Location/Information:

Cuijk, Netherlands