

## TECHNICAL SPECIFICATION NOVOLIN TYPE 20PPO325

<b>Composition</b>	<b>A carded spunbonded fibre. 100% polypropylene. Hydrophobic nonwoven impregnated with a medicinal oil.</b>
--------------------	--

	<b>U.M.</b>	<b>Value</b>
<b>Weight (impr.)</b>	(g/sqm)	20 ± 1
<b>Impregnation</b>	(%)	10 – 12
<b>Thickness (non-impr)</b>	(mm)	0,2
<b>Tensile strength MD</b>	(N/50mm)	33
<b>Tensile strength CD</b>	(N/50mm)	10
<b>Elongation MD</b>	(%)	40 max
<b>Elongation CD</b>	(%)	80 max

### PROCESS PARAMETERS

<b>Speed</b>	(m/min)	100
<b>Pressure</b>	(kg/cm)	70
<b>Temperature</b> Patterned roll	(°C)	150
<b>Temperature</b> Smooth roll	(°C)	145

All tests are carried out according to EDANA recommended tests methods on dry nonwoven. Average values from 50 single tests min.

**Personal / environment protection** : Not applicable

**Handling and storage** : Normal requirement

**First-Aid measures** : No specific measures to be taken